







silicon and tin, and a positive electrode structure comprising one or more compounds selected from the group consisting of lithium manganese oxides, lithium cobalt oxides and lithium nickel oxides.

12. (Previously Presented) The method according to claim 1, in which the dissolution temperature  $T_{\text{dissol}}$  is in the range 45-80°C and the gelling temperature  $T_{\text{gel}}$  is in the range 75-100°C, with the proviso that  $T_{\text{gel}}$  should be higher than  $T_{\text{dissol}}$ .

13. (Previously Presented) The method according to claim 1, in which the electrochemical cell is wound prior to electrolyte impregnation.

14. (Previously Presented) The method according to claim 1, in which the electrolyte incorporation is carried out by pouring or injection.

15. (Previously Presented) The method according to claim 1, in which the electrodes display such a porosity which is such as to allow diffusion of a relatively solvent-rich electrolyte phase into the pores of the electrodes, leaving a relatively polymer-rich electrolyte phase in the volume between the electrodes.

16. (Previously Presented) The method according to claim 1 wherein the gap between electrode laminates of the electrochemical cell is smaller than at least the largest polymer particles so that the electrolyte in the vicinity of the edge of the laminate and outside the laminate contains a larger amount of polymer than the electrolyte between the electrodes.

17. (Canceled)

18. (Previously Presented) The method according to claim 4, wherein the copolymer of vinylidene fluoride and hexafluoropropylene has a molecular weight in the range of 100,000-300,000.

19. (Currently Amended) The method according to claim 5, wherein the electrolyte comprises one or more solvents selected from the group consisting of

- (a) alicyclic carbonates selected from the group consisting of ethylene carbonate and propylene carbonate;
- (b) aliphatic carbonates selected from the group consisting of dimethyl carbonate and diethyl carbonate;
- (c) lactones selected from the group consisting of  $\gamma$ -valerolactone and  $\gamma$ -butyrolactone;
- (d) esters selected from the group consisting of (2-methoxyethylacetate) and ethylacetate; and
- (e) glymes wherein  $R_{20}$  and  $R_{22}$  are methyl and  $R_{23}$ ,  $R_{24}$ ,  $R_{25}$  and  $R_{26}$  are hydrogen.

20. (Previously Presented) The method according to claim 7, wherein the electrolyte comprises solvent(s), salt(s) and polymer in the compositional range 75:17:8 to 88:8:4 percent of the total weight of the electrolyte system.

21. (Previously Presented) The method according to claim 8, wherein the separator consists of a porous structure made of a polymer selected from the group consisting of polyethylene, polypropylene, polycarbonate, and cellulose.

22. (Previously Presented) The method according to claim 10, wherein the thickness is 10-25  $\mu\text{m}$ .

23. (Previously Presented) The method according to claim 11, wherein the negative electrode structure comprises one or more compounds selected from the group consisting of graphite and mesocarbon microbeads; and the positive electrode structure comprises  $\text{LiMn}_2\text{O}_4$  of spinel structure.

24. (Previously Presented) The method according to claim 12, wherein  $T_{\text{dissol}}$  is in the range 65-75°C, and  $T_{\text{gel}}$  is in the range of 80-90°C.

25. (Previously Presented) The method according to claim 6, wherein the electrolyte comprises one or more salts selected from the group consisting of  $\text{LiPF}_6$  and  $\text{LiBF}_4$ .

26. (Currently Amended) ~~The~~ An electrochemical cell according to claim 17, having (i) a negative electrode structure comprising one or more compounds selected from the group consisting of graphite, coke and mesocarbon microbeads, ~~wherein the~~ (ii) a positive electrode structure comprising ~~comprises~~ lithium manganese manganese oxide, and (iii) a gelled polymer electrolyte, 1-12% by weight of the total weight of the electrolyte being said polymer, wherein said polymer is a homopolymer or copolymer selected from the group of monomers consisting of vinyl fluoride, vinylidene fluoride, trifluoroethylene, tetrafluoroethylene and hexafluoropropylene, said electrochemical cell being obtained by or being obtainable by a method comprising:

(a) heating an electrolyte precursor, comprising one or more solvents, one or more salts and a polymer which dissolves in the solvent at a first temperature,  $T_{\text{dissol}}$ , and which is



